

SELECTION & SPECIFICATION DATA

Type	Polymer Modified Asphalt Emulsion
Description	A trowel and spray grade blend of polymer and emulsified asphalts that provide a tough, monolithic, rubberized waterproof membrane on steel, cementitious, modified bitumen and other substrates.
Features	<ul style="list-style-type: none"> • Water-based with low VOCs • High elongation and tensile strength • Puncture resistant • Low permeation rates • Excellent chemical resistance • Sag resistant • Easily repairable
Uses	<ul style="list-style-type: none"> • Waterproofing • Roofing • Moisture/vapor barrier • Secondary containment • Tank chime sealant • Retainage ponds
Color	Black
Finish	Matte
Primer	Self-priming
Dry Film Thickness (DFT)	10 - 30 mils per coat
Solids Content	57% by weight 55% by volume
Maximum Dry Temperature Resistance	300°F (149°C)
Limitations	Protect from freezing

SUBSTRATES & SURFACE PREPARATION

All	Substrate must be clean, dry and free of contaminants.
Previously Painted Surfaces	Consult with ErgonArmor Technical Service.

MIXING & THINNING

Mixing	Not required
Thinning	Do not thin
Ratio	Single component

APPLICATION GUIDANCE

Spray Application	Ertech 3037 is designed for brush, roller, trowel, or airless spray equipment.
Airless Spray	For best results under a wide variety of spray conditions, a 30:1 or higher ratio pump is recommended.
Tip Size	0.025-inch orifice
Hose L/D	200 ft (max) x 3/8-inch diameter
Whip L/D	6 ft (max) x 1/4-inch diameter
Film Thickness	A film thickness of up to 45 mils wet can be achieved on vertical surfaces without sagging.
Brush/Roller	Can be brush or roller applied.
Temperature	Use in temperatures of 50°F (10°C) or higher for best performance.
Dry-To-Touch	2 - 4 hours at 77°F (25°C). Dry times are decreased with air movement over the coating.
Full Cure	24 - 48 hours at 77°F (25°C). Cure times are decreased with air movement over the coating.

PACKAGING, ESTIMATING & HANDLING

ITEM#	PACKAGING
M-3037-000-001	Bulk - LB
M-3037-005-001	Pail - 5 gallons
M-3037-053-001	Drum - 53 gallons
Theoretical Coverage	898 square feet per gallon at 1 mil DFT
Storage & Shelf Life	Estimated shelf life is 6 months when stored in a dry area at 75°F (24°C). Actual shelf life may vary with storage conditions. Do not store below 50°F (10°C) or above 95°F (35°C). Protect from freezing. Do not store product outside. Store indoors.

SAFETY

Safety	Mixes and applications of this product present a number of hazards. Read and follow the hazard information, precautions and first aid directions on the individual product labels and safety data sheets before using.
Ventilation	Use in well ventilated areas.

TYPICAL PHYSICAL PROPERTIES

Density ASTM D1475-13	8.7 lbs/gal
Solids by weight ASTM D5201-05a	57%
Solids by volume ASTM D5201-05a	55%
Specific gravity	1.04
Dry-to-touch, 77°F (25°C) ASTM D5895-96	2 - 4 hours
Full cure, 77°F (25°C)	24 - 48 hours
Viscosity, 77°F (25°C) ASTM D2983-19	75,000 cps
Resistance to oils, greases and solvents	Poor
VOC	0.2 lbs/gal maximum
Permeance 60 mils nominal ASTM E96 A method	0.14 perms
Permeance 60 mils nominal ASTM E96 B method	0.08 perms
Hydrostatic pressure resistance 60mils nominal ASTM C1360	39.2 psi
Low temperature crack bridging 60 mils nominal ASTM C836	Pass
Immersion test 60 mils nominal ASTM D870-09	Pass
Tensile strength ASTM D2370-16	87 psi
Elongation ASTM D412-16	>1,573%

Rev. 09/2025

TERMS AND CONDITIONS OF SALE

While statements, technical information and recommendations contained herein are based on information our company believes to be reliable, nothing contained herein shall constitute any warranty, express or implied, with respect to the products and/or services described herein and any such warranties are expressly disclaimed. We recommend that the prospective purchaser or user independently determine the suitability of our product(s) for their intended use. No statement, information or recommendation with respect to our products, whether contained herein or otherwise communicated, shall be legally binding upon us unless expressly set forth in a written agreement between us and the purchaser/user. For all Terms and Conditions of Sale see ergonarmor.com.